

## VapourTech® Brane® VHP

Product Code: VHP

### Vapour permeable wall insulation

For moisture control behind all types of cladding and in all wall systems in Climate Zones 2-8



VapourTech® Brane® VHP is a Very High Permeance (VHP), vapour permeable, triple-layer, Light Wall Duty wall wrap designed for use in a wide range of wall systems.

VapourTech® Brane® VHP is classified as a Water Barrier and Class 4 Vapour Permeable membrane. Very high levels of water vapour are allowed to absorb and diffuse through the core non-woven structure, ensuring that condensation risk is controlled, while outside liquid water cannot penetrate inwards. VapourTech® Brane® VHP is chemically non-reactive in conjunction with treated timber and salt conditions close to coastlines.

- > Class 4 Vapour Permeable
- > Water Barrier
- > 30 days UV exposure
- > Triple layer construction for durability
- > Low Flammability, suitable for all BALs in bushfire-prone areas

### Application

VapourTech® Brane® VHP is used as a wall wrap behind all types of cladding and in all wall systems in Climate Zone 2-8


NOTE: It is NOT recommended for this application in ABCB Climate Zone 1; select from our range of Class 1 and 2 Vapour Barrier products instead.

VapourTech® Brane® VHP is available in 1.37 m and 1.5 m width rolls, and a convenient 2.74 m width roll that halves installation time and reduces the amount of air gaps and joins in the wall system.

If installed behind non-absorbent claddings such as steel, provision should be given for adequate drainage of any trapped moisture.

### Construction

VapourTech® Brane® VHP is made with an advanced three-layer construction: two tough outer layers of spun-bonded fabric protecting an inner core of VHP membrane.



- > Non-woven Polymer Fabric
- > Very high permeable membrane
- > Non-woven Polymer Fabric

### Declared Total System R-Values

#### Light Weight Cladding

fixed to battens with VapourTech® Brane® VHP + R2.7 fibrous batt.

Winter **R, 2.92**

Summer **R, 2.77**

#### Brick Veneer Wall

with VapourTech® Brane® VHP + R2.7 fibrous batt.

Winter **R, 2.93**

Summer **R, 2.78**

R-values apply to typical conditions for mainland Australian capital cities and have been calculated by an independent consulting engineer in accordance with AS/NZS 4859.1:2018. For detailed design of building systems, seek advice based on actual site conditions from a qualified licensed engineer. The contribution of this product to the total system R-value depends on installation and environmental conditions.

## Material Properties and Classifications

VapourTech® Brane® VHP classifications in accordance with AS/NZS 4200.1:2017.

Criteria	Reference	Result	Requirement
Flammability Index	AS 1530.2-1993	Low $\leq 5$	High ( $> 5$ ) / Low ( $\leq 5$ )
Nominal Thickness		0.38 mm	Value
Duty	AS/NZS 4200.1:2017	Light Wall	Classification
Burst Strength	AS 2001.2.19-1998	254 N	$\geq 200$ N
Edge Tear Machine Direction	TAPPI T 470 om-89	180 N	Min 45 N
Edge Tear Lateral Direction	TAPPI T 470 om-89	89 N	Min 45 N
Vapour Control	ASTM E96	Class 4 Vapour Permeable	Class 1 to 4
Vapour Permeance	ASTM E96	12.848 $\mu\text{g}/\text{N}\cdot\text{s}$	Value
Water Control	AS/NZS 4201.4:1994	Water Barrier	Classification
Resistance to Dry Delamination	AS/NZS 4201.1:1994	Pass	Pass
Resistance to Wet Delamination	AS/NZS 4201.2:1994	Pass	Pass
Shrinkage (Repeated wetting & drying)	AS/NZS 4201.3:1994	0.0%	$< 0.5\%$
Electrical Conductivity	AS/NZS 4200.1:2017	Non-conductive	Classification
Emittance Value	AS/NZS 4201.5:1994	0.9, 0.9	Value
Emittance Classification	AS/NZS 4200.1:2017	IR Non-reflective, IR Non-reflective	Classification
Emittance Category	AS/NZS 4200.1:2017	NN	Category

### NCC Compliant

VapourTech® Brane® VHP complies with AS/NZS 4200.1:2017 and therefore meets all of the requirements of the *National Construction Code* of Australia for pliable building membranes, insulation and sarking-type materials.

### Fire Performance

#### Flammability Index

Low ( $\leq 5$ )

Tested in accordance with AS1530.2-1993 - *Methods for fire tests on building materials, components and structures Part 2: Test for flammability of materials*.

#### Bushfire Attack Levels

Complies with AS3959-2018 *Construction of buildings in bushfire-prone areas* for use in all BALs.

Seek independent advice regarding the selection of sarking prior to installation in the BAL design.

### Dimensions

2740 mm x 30 m (82.2 m<sup>2</sup>)

1500 mm x 30 m (45 m<sup>2</sup>)

1370 mm x 30 m (41.1 m<sup>2</sup>)

Nominal Thickness: 0.38 mm

### Specification Notes

When specifying, state the following:

Product Name: Ametalin VapourTech® Brane® VHP

The pliable building membrane to be installed shall be Ametalin VapourTech® Brane® VHP, very high permeance wall wrap and shall be installed in accordance with AS 4200.2: 2017 *Pliable Building Membranes and Underlays, Part 2: Installation*.

Emittance Value: 0.9, 0.9

Emittance Classification: IR Non-Reflective, IR Non-Reflective

Vapour Control Classification: Class 4 Vapour Permeable, 12.848  $\mu\text{g}/\text{N}\cdot\text{s}$

Water Control Classification: Water Barrier

Flammability Classification: Low ( $\leq 5$ )

Duty Classification: Light Wall in accordance with AS/NZS 4200.1:2017

Complete details available on our website:

<https://www.ametalin.com>

### Handling and Storage

Store this product undercover in a clean, dry place in the pack provided.

### Performance insulation for a greener world

9-11 Playford Crescent Salisbury North SA 5108

T: +61 8 8285 6955 F: +61 8 8285 5911

E: [info@ametalin.com](mailto:info@ametalin.com) W: [ametalin.com](http://ametalin.com)



Durability may be affected by environmental factors, including chemical and airborne pollutants, if used in industrial or farm buildings.

Australian designed for Australian conditions. Ametalin 9-11 Playford Crescent, Salisbury North SA 5108 T: +61 8 8285 6955 F: +61 8 8285 5911 E: [info@ametalin.com](mailto:info@ametalin.com)

© 2023 Ametalin All Rights Reserved. Ametalin is a division of Amalgamated Metal Industries Pty. Ltd. Product information in this publication and otherwise supplied to users is based on our general experience and is given in good faith, but due to factors outside our knowledge and control which may affect the use of products, no warranty is given or implied with respect to this information or the product itself regarding the suitability of the product for any particular purpose. The usage of this and other building membranes will affect moisture migration in the building element. The purchaser should independently determine the suitability of the product for the intended purpose. For large projects with complex air-conditioning and condensation issues, designers may wish to contact our technical department. Product colour may vary from batch to batch. Amalgamated Metal Industries Pty. Ltd. reserves the right to amend product specifications without prior notice. Information provided is considered to be true and correct at the time of publication. Complete details including installation instructions are available on our website: [www.ametalin.com](http://www.ametalin.com) APM-23173-0